

Josephson Effect in Superconductors with Odd-Gap Pairing

M.V.Sadovskii

Institute for Electrophysics, Russian Academy of Sciences,

Ural Branch, Ekaterinburg 620219, Russia

E-mail: sadovski@ief.e-burg.su

Abstract

It is shown that the Josephson current in $S-I-S$ —geometry is zero, if one or both superconductors possess the gap odd over $p-p_F$. For the odd-frequency pairing the Josephson current is zero in case of the tunneling between the traditional and odd-gap superconductor and is finite for the tunneling between two odd-gap superconductors.

PACS numbers: 74.20.Fg, 74.50.+r

Recently a number of non-traditional models of the so called odd-gap pairing in superconductors were actively studied by a number of authors [1–5]. These are attractive as possible models for the interpretation of the physical properties of some existing unusual superconductors (high- T_c , heavy-fermion) as well as from the point of view of the search of the new systems with anomalous properties of superconducting state. It is most important to formulate some simple experimental criteria which will enable an unambiguous determination of the type of corresponding anomalous pairing.

The aim of the present note is to analyze some simple anomalies of Josephson tunneling in $S - I - S$ structures with odd-gap superconductors. We shall start with the standard approach to Josephson effect within the formalism of tunneling Hamiltonian [6]. This shows that the expression for the Josephson current through the tunneling contact can be represented in the following form:

$$I = I_c \sin(\phi_1 - \phi_2) \quad (1)$$

where ϕ_1 and ϕ_2 — are the phases of superconducting order-parameter (gap) in S -contacts 1 and 2, and the critical current I_c is defined by the general expression as:

$$I_c = 4e \sum_{\mathbf{p}\mathbf{q}} |T_{\mathbf{p}\mathbf{q}}|^2 T \sum_{\omega_n} F_1^*(\mathbf{p}, \omega_n) F_2(\mathbf{q}, -\omega_n) \quad (2)$$

where $T_{\mathbf{p}\mathbf{q}}$ —is the tunneling matrix element for electrons through the insulating layer, while the anomalous Matsubara-Gorkov functions $F_{1,2}(\mathbf{p}, \omega_n)$ are determined by:

$$F(\mathbf{p}, \omega_n) = \frac{\Delta(\mathbf{p}, \omega_n)}{\omega_n^2 + \xi_{\mathbf{p}}^2 + \Delta^2(\mathbf{p}, \omega_n)} \quad (3)$$

Here $\Delta(\mathbf{p}, \omega_n)$ —is the gap function, $\omega_n = (2n + 1)\pi T$ (T —temperature), e —electronic charge, $\xi(\mathbf{p}) = v_F(|\mathbf{p}| - p_F)$ —electronic excitation energy close to the Fermi level in the normal state of a superconductor.

Consider first the pairing odd over $p - p_F$ [1,3,4]. In this case we obtain:

$$\Delta(\mathbf{p}, \omega_n) = \Delta(\xi_{\mathbf{p}}) = -\Delta(-\xi_{\mathbf{p}}) \quad (4)$$

The pairing is isotropic and Eq.(2) is reduced as usual to the following form [6]:

$$I_c = \frac{T}{\pi e R} \sum_{\omega_n} \int_{-\infty}^{\infty} d\xi_p \int_{-\infty}^{\infty} d\xi_q F_1^*(\xi_p, \omega_n) F_2(\xi_q, -\omega_n) \quad (5)$$

where R —is the resistance of tunneling contact, expressed via the matrix element $T_{\mathbf{p}\mathbf{q}}$ averaged over the Fermi surfaces of both superconductors. It is easy to see that Eq.(5) is actually zero due to the odd nature of $\Delta(\xi_p)$ over the variable ξ_p (4), both when only one of superconductors has an odd gap and when both S -contacts are odd. Of course, the transition from Eq.(2) to Eq.(5) and the previous statement are valid only if we neglect the change of the tunneling matrix element $T_{\mathbf{p}\mathbf{q}}$ on the scale of the order of Fermi energy E_F and I_c is actually zero neglecting the contribution of the order of T_{pq}^2/E_F^2 . From experimental point of view this means almost total suppression of Josephson tunneling.

Consider now the case odd-frequency pairing [2,3,5]. In this case

$$\Delta(\mathbf{p}, \omega_n) = -\Delta(\mathbf{p}, -\omega_n) \quad (6)$$

Then from the general expression (2) it is clear that I_c is zero in case when one of S -contacts is the odd-gap superconductor. When both contacts are odd we obtain the finite expression for I_c the explicit form of which will depend on the specific model of odd-frequency pairing [2,5]. This may be used to study the properties of the appropriate order-parameter. The vanishing of Josephson current in the case of contacts of different parity is connected here with the fact that the odd-frequency gap breaks the T -symmetry, while the tunneling Hamiltonian is obviously invariant against the time-reversal [6].

This work is supported by the State Program of Research on High-Temperature Superconductivity in the framework of Project N° 93-001.

REFERENCES

- [1] F.Mila, E.Abrahams. Phys.Rev.Lett. **67**, 2379 (1991)
- [2] A.Balatsky, E.Abrahams. Phys.Rev. **B45**, 13125 (1992)
- [3] E.Abrahams. J.Phys.Chem.Solids **53**, 1487 (1992)
- [4] E.Z.Kuchinskii, M.V.Sadovskii, M.A.Erkabaev. JETP **77**, 692 (1993)
- [5] P.Coleman, E.Miranda, A.Tsvelik. Phys.Rev. **B49**, 8995 (1994)
- [6] I.O.Kulik, I.K.Yanson. Josephson Effect in Superconducting Tunneling Structures.
"Nauka", Moscow, 1970, (In Russian).